

## IN THE CLAIMS:

Please amend claims as follows:

1. (original) A copper-based alloy excellent in dezincing resistance comprising, in percentage by weight:

Cu : 57 – 69%,

Sn : 0.3 – 3%

Si : 0.02 – 1.5%,

Bi : 0.5 – 3%, and

Pb : not more than 0.2% (including 0%),

where the ratio of Si/Sn expressed in weight percentage is in the range of 0.05 – 1 and apparent zinc content as defined by Formula (1) below is in the range of more than 39 – 50 wt.%, and

the balance of unavoidable impurities:

Apparent Zn content =  $[(\text{Zn}\% + 2.0 \times \text{Sn}\% + 10.0 \times \text{Si}\%) / (\text{Cu}\% + \text{Zn}\% + 2.0 \times \text{Sn}\% + 10.0 \times \text{Si}\%)] \times 100$  ... (1).

2. (original) A copper-based alloy excellent in dezincing resistance comprising, in percentage by weight:

Cu : 57 – 69%,

Sn : 0.3 – 3%

Si : 0.02 – 1.5%,

Bi : 0.5 – 3%, and

Pb : not more than 0.2% (including 0%),

further containing, in percentage by weight,

at least one of P : 0.02 – 0.2%, Sb : 0.02 – 0.2% and As : 0.02 – 0.2% at a total content of 0.02 – 0.2%,

where the ratio of Si/Sn expressed in weight percentage is in the range of 0.05 – 1 and apparent zinc content as defined by Formula (1) below is in the range of more than 39 – 50 wt.%, and

the balance of unavoidable impurities:

Apparent Zn content =  $[(\text{Zn}\% + 2.0 \times \text{Sn}\% + 10.0 \times \text{Si}\%) / (\text{Cu}\% + \text{Zn}\% + 2.0 \times \text{Sn}\% + 10.0 \times \text{Si}\%)] \times 100$  ... (1).

3. (original) A copper-based alloy excellent in dezincing resistance comprising, in percentage by weight:

Cu : 57 – 69%,

Sn : 0.3 – 3%

Si : 0.02 – 1.5%,

Bi : 0.5 – 3%, and

Pb : not more than 0.2% (including 0%),

further containing, in percentage by weight,

at least one of Fe : 0.01 – 0.5%, Ni : 0.01 – 0.5%, Mn : 0.01 – 0.5%, Al : 0.01 – 0.5%, Cr : 0.01 – 0.5%, Be : 0.01 – 0.5%, Zr : 0.01 – 0.5%, Ce : 0.01 – 0.5%, Ag : 0.01 – 0.5%, Ti : 0.01 – 0.5%, Mg : 0.01 – 0.5%, Co : 0.01 – 0.5%, Te : 0.01 – 0.2%, Au : 0.01 – 0.5%, Y : 0.01 – 0.5%, La : 0.01 – 0.5%, Cd : 0.01 – 0.2%, Ca : 0.01 – 0.5% and B : 0.01 – 0.5% at a total content of 0.01 – 3%,

where the ratio of Si/Sn expressed in weight percentage is in the range of 0.05 – 1 and apparent zinc content as defined by Formula (1) below is in the range of more than 39 – 50 wt.%, and

the balance of unavoidable impurities:

$$\text{Apparent Zn content} = [(Zn\% + 2.0 \times Sn\% + 10.0 \times Si\%) / (Cu\% + Zn\% + 2.0 \times Sn\% + 10.0 \times Si\%)] \times 100 \quad \dots (1).$$

4. (original) A copper-based alloy excellent in dezincing resistance comprising, in percentage by weight

Cu : 57 – 69%,

Sn : 0.3 – 3%

Si : 0.02 – 1.5%,

Bi : 0.5 – 3%,

Pb : not more than 0.2% (including 0%),

at least one of P : 0.02 – 0.2%, Sb : 0.02 – 0.2% and As : 0.02 – 0.2% at a total content of 0.02 – 0.2%, and

at least one of Fe : 0.01 – 0.5%, Ni : 0.01 – 0.5%, Mn : 0.01 – 0.5%, Al : 0.01 – 0.5%, Cr : 0.01 – 0.5%, Be : 0.01 – 0.5%, Zr : 0.01 – 0.5%, Ce : 0.01 – 0.5%, Ag : 0.01 – 0.5%, Ti : 0.01 – 0.5%, Mg : 0.01 – 0.5%, Co : 0.01 – 0.5%, Te : 0.01 – 0.2%, Au : 0.01 – 0.5%, Y : 0.01 – 0.5%, La : 0.01 – 0.5%, Cd : 0.01 – 0.2%, Ca : 0.01 – 0.5% and B : 0.01 – 0.5% at a total content of 0.01 – 3%,

where the ratio of Si/Sn expressed in weight percentage is in the range of 0.05 – 1 and apparent zinc content as defined by Formula (1) below is in the range of more than 39 – 50 wt.%, and

the balance of unavoidable impurities:

$$\text{Apparent Zn content} = [(Zn\% + 2.0 \times Sn\% + 10.0 \times Si\%) / (Cu\% + Zn\% + 2.0 \times Sn\% + 10.0 \times Si\%)] \times 100 \quad \dots (1).$$

5. (once amended) A copper-based alloy excellent in dezincing resistance according to ~~any of claims 1 to 4~~, wherein one or both of Si-system leadless brass scrap and Bi-system leadless brass scrap are used as source starting material for Si and Bi, respectively.

6. (new) A copper-based alloy excellent in dezincing resistance according to claim 2, wherein one or both of Si-system leadless brass scrap and Bi-system leadless brass scrap are used as source starting material for Si and Bi, respectively.

7. (new) A copper-based alloy excellent in dezincing resistance according to claim 3, wherein one or both of Si-system leadless brass scrap and Bi-system leadless brass scrap are used as source starting material for Si and Bi, respectively.

8. (new) A copper-based alloy excellent in dezincing resistance according to claim 4, wherein one or both of Si-system leadless brass scrap and Bi-system leadless brass scrap are used as source starting material for Si and Bi, respectively.